



Brut

Kvadrat Divina



F-506
(120)
light grey



Composition
100% new wool

Pilling
3, EN ISO 12945

Flame resistance
EN 1021-1/2
BS 5852, ig. s. 2-5
DIN 4102 B2 - ÖNORM B1/Q1
NF D 60 013 - UNI 9175, 11M
US Cal. Tech. Bull. 117 - A.652
(16)

Abrasion
45 000 Martindale


Lightfastness
5-7 (ISO 105-B02)

Kvadrat Vidar



AS1 (143)	AS2 (152)	AS3 (182)	AS4 (222)	AS5 (443)	AS6 (554)	AS7 (582)	AS8 (622)	AS10 (872)	AS11 (932)	AS12 (1062)	AS13 (1880)	AS15 (733)
---------------------	---------------------	---------------------	---------------------	---------------------	---------------------	---------------------	---------------------	----------------------	----------------------	-----------------------	-----------------------	----------------------

Torri Lana Rico



AT1 70 anthracite grey	AT 80 white	AT 130 grey	AT 270 yellow	AT 280 red	AT 300 pink	AT 360 orange	AT 420 green
--	--------------------------	--------------------------	----------------------------	-------------------------	--------------------------	----------------------------	---------------------------



Composition
94% new wool
6% polyamide

Pilling
Note 4, EN ISO 12945

Flame resistance
EN 1021-1/2
BS 5852 ignition source 2-3
DIN 4102 B2, NF D 60 013
UNI 9175 11M
US Cal. Tech. Bull. 117 IMO
Crib 5 when flame protected

Abrasion
100 000 Martindale

Lightfastness
Note 5-7, ISO 105-B02

Glamour Azimut



BC1 (400) ocher	BC (302) orange	BC (700) pink	BC (901) white	BC (800) black
------------------------------	------------------------------	----------------------------	-----------------------------	-----------------------------



Composition
56% Cotton
30% Viscose
14% Linen

Pilling
BS EN ISO 12945-2:2002 (3/4)

Flame resistance
BS 5852
Cigarette test EN 1021-1

Abrasion
36 000 Martindale

Lightfastness
BS EN ISO 105-B02 (4-5 / 5)

Glamour Amby



BF (1) grey	BF (2) white	BF (3) light grey	BF (4) grey	BF (5) anthracite grey	BF (6) ocher
--------------------------	---------------------------	--------------------------------	--------------------------	--	---------------------------



Composition
92% Polyester (PES)
5% cotton
3% wool

Pilling
Note 5, ISO 12945

Flame resistance
BS 5852
Cigarette test EN 1021-1

Abrasion
100 000 Martindale

Lightfastness
Note 5, ISO 105-B02

Glamour Globo



BE (1) grey	BE (2) white	BE (3) light grey	BE (4) grey	BE (5) anthracite grey	BE (6) ocher
--------------------------	---------------------------	--------------------------------	--------------------------	--	---------------------------



Composition
30% acrilico (PC)
30% viscosa (VI)
20% lana (WO)
12% poliestere (PL)
8% cotone (CO)

Pilling
Note 3-4, ISO 12945

Flame resistance
BS 5852
Cigarette test EN 1021-1

Abrasion
21 000 Martindale

Lightfastness
Note 5, ISO 105-B02

Glamour Shee



BG (1) grey	BG (2) white	BG (3) light grey	BG (4) grey	BG (5) anthracite grey	BG (6) ocher
--------------------------	---------------------------	--------------------------------	--------------------------	--	---------------------------



Composition
30% acrilico (PC)
30% viscosa (VI)
20% lana (WO)
12% poliestere (PL)
8% cotone (CO)

Pilling
Note 3-4, ISO 12945

Flame resistance
BS 5852
Cigarette test EN 1021-1

Abrasion
21 000 Martindale

Lightfastness
Note 5, ISO 105-B02



Composition
30% acrilico (PC)
30% viscosa (VI)
20% lana (WO)
12% poliestere (PL)
8% cotone (CO)

Pilling
Note 3-4, ISO 12945

Flame resistance
BS 5852
Cigarette test EN 1021-1

Abrasion
21 000 Martindale

Lightfastness
Note 5, ISO 105-B02